



## Technical Data Sheet

**SUSTARIN® H AF - DE588 - ASTM** (Acetal (Delrin®) AF - DE588)

### Product characteristics

- Good dimensional stability
- Very good sliding properties
- Very wear resistant

### Product applications

- Mechanical engineering
- Electrical industry
- Materials handling industry

	Test method	Unit	Value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.54
Water Absorption	ASTM D570	%	0.8
Water Absorption 24 hours	ASTM D570	%	0.2
Dissipation Factor	ASTM D150	1MHz	0.009
<b>Mechanical properties</b>			
Tensile Strength at Yield	ASTM D638	psi	6630
Hardness	ASTM D2240	Shore D	76
Tensile Modulus	ASTM D638	psi	540000
Tensile Elongation	ASTM D638	%	30
Flexural Strength	ASTM D790	psi	12500
Flexural Modulus	ASTM D790	psi	405000
Compressive Strength	ASTM D695	psi	12600
Rockwell Hardness	ASTM D785	M	50
Rockwell Hardness	ASTM D785	R	110
<b>Thermal properties</b>			
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	4.4
Continuous Service Temperature, Air		°F	185
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	244
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	334
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	2.0
Flammability, UL94		1/8 inch	HB
Melting Point	ASTM D789	°F	350
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1 MHz	3.1
Dielectric strength	ASTM D149	V/mil	400
Surface resistivity	ASTM D257	Ω/cm	10 <sup>16</sup>
<b>Compliance Properties</b>			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.