



PEEK 5025Ä

COMPRESSION MOLDED

PEEK 5025Ä is a proprietary, bearing grade PEEK (polyetheretherketone) material, reinforced with carbon fibers and internally lubricated with different proprietary lubricants to improve dry running capabilities. Tribological evaluations under dry running conditions have shown its friction coefficient and wear rate to be much lower than other bearing grade composite materials available in the market. Its extremely low wear rate along with low coefficient of thermal expansion properties make this material an ideal candidate for replacing metal wear components.

This material is especially suited to centrifugal pump components such as impeller/case wear rings, throat bushings, and line shaft bearings. In addition to improved reliability and increased MTBR (mean time between repair), these features allow for 50% tighter clearance gaps than API recommended values, thereby increasing pump efficiency resulting in substantial savings.

<i>Physical Properties</i>	<i>ASTM Method</i>	<i>Typical Values</i>
Specific Gravity	D792	1.42 gr/cm ³
Water Absorption (24hrs. @73.4°F)	D570	.15 %
Color	N/A	Black

<i>Mechanical Properties</i>		
Tensile Strength	D638	18,900 psi
Tensile Elongation	D638	3.5 %
Flexural Strength	D790	25,000 psi
Flexural Modulus	D790	1.3 10 ⁶ psi
Compressive Strength	D695	25,000 psi
Compressive Modulus	D695	540,000 psi
Impact Strength (Izod, notched)	D256	1.5 ft-lb/in
Hardness	Shore D	88

<i>Tribological Properties</i>		
Coefficient of Friction		
Static	D3702	0.12
Dynamic	D3702	0.08
Limiting PV (200 psi, dry)	D3702	120,000+ psi-fpm
Wear Rate (PV: 20,000 psi-fpm)	D3702	0.80 µin/min

<i>Thermal Properties</i>		
Thermal Conductivity		0.62 W/m.K
Coefficient of Linear Thermal Expansion		
	78 to 200 °F	9 10 ⁻⁶ /°F
	200 to 300 °F	11
	300 to 400 °F	22
Heat Deflection Temperature (264psi)	D648	450 °F
Glass Transition Temperature (T _g)	D3418	289 °F
Continuous Service Temperature (Max @ no load)		500 °F
Melting Point		644 °F

<i>Electrical Properties</i>		
Volume Resistivity	D257	10 ⁵ ohm-cm
Dielectric Strength	D149	KV/mm
Dielectric Constant	D150	50Hz, 200°C

Note: Property values should be interpreted as typical rather than minimum value. All technical information and recommendations are presented in good faith, based upon laboratory and real-world tests believed to be reliable and practical. However, Vertec Polymers cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine product suitability to any given application.